



TESTS	STANDARD	PROPERTY OR ATTRIBUTE	MEASURE UNIT	RESULTS
1. INSPECTION REQUIREMENTS				
Colour, pattern and surface finish	EN 438-8 Part 5.2.2.3	Due to the fact that wood is a natural product, each veneer may be considered as unique. Colour and structure differences are considered as normal. Singularities such as knots and resin inclusions are not considered as defects, but as a part of the décor. There are differences in light fastness performances depending on the wood species and the source of the wood.		
2. DIMENSIONAL TOLERANCES				
<div style="display: flex; justify-content: space-around; align-items: center;"> <div style="text-align: center;">  <p>2440 595</p> </div> <div style="text-align: center;">  <p>595 1220</p> </div> </div>				
Dimensions				
Thickness	-	6	mm	± 0,4
		330		±10%
		500		±10%
Curvature radius	-	1000	mm	±10%
		2000		±10%
		4000		±10%
Length and width	-	2440x595	mm	+10/-0
		595x1220		+10/-0
3. PHYSICAL PROPERTIES				
Resistance to impact with large diameter ball	EN 438-2 Part 21	Maximum height for which no visible surface cracking or imprint greater than 10mm	mm	≥ 1.800
Determination of graffiti resistance	ASTM D 6578	Cleanability level		
			Permanent blue marker	8
			Solvent based acrylic spray	4
			Solvent based alkyd spray	4
			Wax crayon	10
			Ballpoint ink	8
			Water based ink black marker	10
4. WEATHER RESISTANCE REQUIREMENTS				
Resistance to UV light	EN 438-2 Part 28 Rating according to EN 20105 – A02	Contrast	Grey scale rating	≥ 3
		Aspect	Rating	≥ 4
Resistance to artificial weathering (including light fastness)	EN 438-2 Part 29 Rating according to EN 20105 – A02	Contrast	Grey scale rating	≥ 3
		Appearance	Rating	≥ 4
5. CE SAFETY REQUIREMENTS				
Water vapour permeability	EN 438-7 Part 4.4	Wet cup method		110
		Dry cup method	μ	250
Resistance to fixings	EN 438-7 Part 4.5	Screw holding value	N	2.000
Density	EN ISO 1.183	Density	g/cm ³	≥ 1,35
Resistance to wet conditions	EN 438-2 Part 15	Moisture absorbed	%	≤ 5
		Appearance	Rating	≥ 4
6. CE SAFETY REQUIREMENTS - REACTION TO FIRE				
Reaction to fire	EN 13.501-1	Euroclase	Classification	D-s2,d0 (1)

(1) CWFT: Classified Without Further Testing according to EN 438 Part 7, 4.2.3.

Screw or rivet fixing is recommended. Other fixing systems must be consulted with technical department.